



Polyurethane spray-coat
top layers

Bonded SBR
base layer

- SEAMLESS
- SPIKE-RESISTANT
- WORLD ATHLETICS CERTIFIED

A seamless, water-permeable athletics surface for training and competition. The certified 13.0 mm system combines an in-situ bonded SBR rubber base with multiple flexible polyurethane spray-coat layers.

TECHNICAL PERFORMANCE

	SR NATIONAL	WA REQUIREMENT
Absolute thickness	13.0 mm	—
Friction	65	> 47
Tensile strength	0.46 MPa	> 0.40 MPa
Elongation at break	48%	> 40%
Impact absorption at 23 °C	40%	35%–50%
Vertical deformation at 23 °C	2.1 mm	0.6–2.5 mm

Spray coat · Water-permeable / porous · World Athletics S-04-0047

Issued 1 March 2026 · Expires February 2030

